

(19) 世界知的所有権機関
国際事務局



(43) 国際公開日
2005年2月17日 (17.02.2005)

PCT

(10) 国際公開番号
WO 2005/014873 A1

- (51) 国際特許分類⁷: C22C 38/00, 38/40, 38/48, C21D 9/46 (74) 代理人: 小倉 亘, 外(OGURA, Wataru et al.); 〒171-0043 東京都豊島区要町三丁目2番7号 大野千川ビル201 Tokyo (JP).
- (21) 国際出願番号: PCT/JP2004/011410
- (22) 国際出願日: 2004年8月3日 (03.08.2004) (81) 指定国(表示のない限り、全ての種類の国内保護が可能): AE, AG, AI, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (25) 国際出願の言語: 日本語
- (26) 国際公開の言語: 日本語
- (30) 優先権データ:
特願2003-287774 2003年8月6日 (06.08.2003) JP
- (71) 出願人(米国を除く全ての指定国について): 日新製鋼株式会社 (NISSHIN STEEL CO., LTD.) [JP/JP]; 〒100-8366 東京都千代田区丸の内三丁目4番1号 Tokyo (JP).
- (72) 発明者: および
- (75) 発明者/出願人(米国についてのみ): 森川 広 (MORIKAWA, Hiroshi) [JP/JP]; 〒746-8666 山口県周南市野村南町4976番地 日新製鋼株式会社 技術研究所内 Yamaguchi (JP). 香月 淳一 (KATSUKI, Junichi) [JP/JP]; 〒746-8666 山口県周南市野村南町4976番地 日新製鋼株式会社 技術研究所内 Yamaguchi (JP). 藤井 孝浩 (FUJII, Takahiro) [JP/JP]; 〒746-8666 山口県周南市野村南町4976番地 日新製鋼株式会社 技術研究所内 Yamaguchi (JP).
- (84) 指定国(表示のない限り、全ての種類の広域保護が可能): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), ユーラシア (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), ヨーロッパ (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- 添付公開書類:
— 国際調査報告書
- 2文字コード及び他の略語については、定期発行される各PCTガゼットの巻頭に掲載されている「コードと略語のガイダンスノート」を参照。

(54) Title: WORK-HARDENED MATERIAL FROM STAINLESS STEEL

(54) 発明の名称: ステンレス鋼の加工硬化材

(57) Abstract: A work-hardened material from a stainless steel sheet, which has a chemical composition, in mass %, that C: 0.15 % or less, Si: 1.0 % or less, Mn: 1.0 % or less, S: 0.005 % or less, Cr: 10 to 20 %, Ni: 0.5 % or less, Al: 0.001 to 0.05 %, and optionally, one or more of Mo: 0.5 to 2.0 %, Cu: 0.5 to 3.0 % and Nb: 0.05 to 1.0 %, wherein Al_2O_3 based and/or $Al_2O_3 \cdot MgO$ based inclusions having a particle diameter $\leq 10 \mu m$ are dispersed in a cleanliness $\leq 0.06 \%$, and the material exhibits enhanced strength due to a work ferrite structure. The above work-hardened material exhibits an 0.2 % offset yield strength as high as 700 N/mm² or higher and also is excellent in bending workability, and thus can be suitably used as parts or a structural material for a household electrical appliance, an OA equipment and the like.

(57) 要約: C:0.15質量%以下, Si:1.0質量%以下, Mn:1.0質量%以下, S:0.005質量%以下, Cr:10~20質量%, Ni:0.5質量%以下, Al:0.001~0.05質量%, 必要に応じてMo:0.5~2.0質量%, Cu:0.5~3.0質量%, Nb:0.05~1.0質量%の1種又は2種以上を含むステンレス鋼板である。粒径 $\leq 10 \mu m$ の Al_2O_3 系及び/又は $Al_2O_3 \cdot MgO$ 系介在物が清浄度 $\leq 0.06\%$ で分散し、加工フェライト組織により高強度化されている。700N/mm²以上の高い0.2%耐力を示しながら曲げ加工性に優れ、軽量化が要求される家電製品, OA機器等の部品, 構造材として使用される。

WO 2005/014873 A1

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP2004/011410

A. CLASSIFICATION OF SUBJECT MATTER

Int.Cl.⁷ C22C38/00, C22C38/40, C22C38/48, C21D9/46

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Int.Cl.⁷ C22C38/00, C22C38/40, C22C38/48, C21D9/46

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Jitsuyo Shinan Koho 1922-1996 Toroku Jitsuyo Shinan Koho 1994-2004

Kokai Jitsuyo Shinan Koho 1971-2004 Jitsuyo Shinan Toroku Koho 1996-2004

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP 4-65141 B2 (Nippon Steel Corp.), 19 October, 1992 (19.10.92), Full text (Family: none)	1-3
A	JP 2-18379 B2 (Nippon Steel Corp.), 25 April, 1990 (25.04.90), Full text (Family: none)	1-3
A	JP 8-246105 A (Nippon Yakin Kogyo Co., Ltd.), 24 September, 1996 (24.09.96), Full text (Family: none)	1-3

☒ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search
27 October, 2004 (27.10.04)Date of mailing of the international search report
16 November, 2004 (16.11.04)Name and mailing address of the ISA/
Japanese Patent Office

Authorized officer

Facsimile No.

Telephone No.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP2004/011410

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP 5-255816 A (NKK Corp.), 05 October, 1993 (05.10.93), Full text (Family: none)	1-3
A	JP 2002-194505 A (Sumitomo Metal Industries, Ltd.), 10 July, 2002 (10.07.02), Full text (Family: none)	1-3